



Care of Chrome

The following care of chrome is essential in **maximising** the life of chrome rods.

All hydraulic cylinders with chrome exposed to the elements must be greased to protect against corrosion.

Chrome must be greased during machine assembly, transportation and storage. Chrome must be inspected every 4 weeks for grease requirements.

NHL use Cromax 280 as standard

Other chrome spec such as:

- Nikrom
- Chrome over Stainless
- Induction Hardened

Are available upon customer request.

It must be carefully noted that all NHL Chrome with the exception of Induction Hardened are only chrome plated and will not withstand external damage such as stones, grinding or welding sparks..

NHL highly recommend the application of;

- CAZAR K
- ADHESIVE WATER
- RESISTANT GREASE

on all exposed chrome.

CARE OF CHROME (cleaning)

Nitric Solvent (without chlorate) is recommended by NHL in any necessary cleaning of chrome.

The use of anything else might harm or reduce the protection of the chrome.



THE END